

# Macrosol F Structural Synthetic Fibres

TECHNICAL DATA SHEET

CF 65/50 SS

## Macrosol – Polypropylene fibres for concrete and mortar reinforcement

### 1. General

#### 1.1 Description:

Macrosol fibres are extruded from a natural virgin Polypropylene homo polymer, formed into a Corrugated profile for concrete and mortar reinforcement and other composite materials

#### 1.2 Qualities

Standard quality

- Polypropylene compound

#### 1.3 Coatings (If Applicable)

#### 1.4 Concept and terms

$L$  : the nominal length in mm,

$d_e$  : the nominal diameter in mm,

Factor  $\lambda$  : the length-to-diameter ratio ( $L/d$ ). This parameter is important to the properties of the concrete or mortar for which Macrosol fibres are used.

### 2. Explanation of used symbols

- Form of delivery: C = Collated  
L = Loose
- Shape of fibre: F = Flat Corrugated Shaped anchorage
- Performance class: is approximately the ( $L/d$ ) = 65
- Length of the fibre: indicative length of the fibre in mm = 50 mm
- Fibre Type: S = Structural Synthetic fibre

#### 2.1 No of fibres per kg

Approximately 68 000 per kg (calculated)

### 3. Properties based on ASTM Requirements

#### 3.1 Nominal fibre diameter ( $d$ ): See table 1

Table 1: Nominal fibre diameter ( $d$ ) and tolerance

$d_e - 0.6$  mm

#### 3.2 Nominal length ( $L$ ): See table 2

Table 2: Nominal length ( $L$ ) and tolerance

$L - 50$  mm

#### 3.3 Tensile strength ( $R/m$ ): See table 3

Table 3: Tensile strength ( $R/m$ ) – N/mm<sup>2</sup>

N – 450 N/mm<sup>2</sup>

#### 3.4 Factor $\lambda$ (Aspect Ratio):

$L/d - 50 \text{ mm} / .6 = 85$

#### 3.5 Melting point (°C)

150 °C to 170 °C

#### 3.6 Fibre density (g/cm<sup>3</sup>)

0.91

#### 3.7 Colour

Translucent or Grey

#### 3.8 Elongation at yield (%)

Between 15 and 25%